## BEVERAGES



1 ANSTONIA

## **XTREMETHENE**



## BEVERAGES

## **XTREMETHENE**

CON E TOUR

Application	Collation shrink application	
	Specification	Tolerance
Material	CO-EX LDPE + LLDPE (redefined blend)	
Material origin	South Africa	
Gauge	20 - 50 Micron	± 10%
Width	75 mm – 2250 mm (plain) 75 mm – 1200 mm (printed)	± 5 mm
COF (Coefficient Of Friction)	0,25	± 0,05
Natural colour	Clear	
Shrinkage		
MD (Machine Direction)	67% - 73%	
TD (Transverse Direction)	15% - 25%	
Appearance	High gloss, good clarity, low haze.	
Static	No cling or snapback	
Core size	76 mm	
Core thickness	10 mm	± 1 mm
Core material	Paper	
Reference to traceability	MCG Flexibles label used	
Reference to packaging	Specification labels on outside of roll and inside the core	
Storage (up to 6 months)	Storage temperatures recommended below 25°C in order to avoid deterioration of the film surface properties. Must be stored away from direct sunlight. Storage conditions must be clean, cool and dry.	
Food packaging	This material complies with FDA regulation 177.1520 and EC Directive 10/2011.	

Durban: Tel: +27 (0)31 460 5800 • 2 Richard Carte Road, Mobeni, Durban Gauteng: Tel: +27 (0)11 677 1200 • No. 2, 33rd Street, Malvern, Johannesburg Cape Town: Tel: +27 (0)21 551 2310 • 16 Bolt Avenue, Montague Gardens Windhoek: Tel: +264 (0)83 330 7340 • 12 Ruhr Street, Northern Industrial Area, Windhoek flexibles@mcgind.co.za • www.mcgindustries.com

